

# EpjStik™ SA-250

## PEEL & STICK ROOFING UNDERLAYMENT



### Technical Data Sheet

TEST PROPERTIES	TEST STANDARD	TYPICAL VALUES
UNROLLABILITY	ASTM D1970	NO CRACKING, TEARING OR DAMAGE
THICKNESS MILS	ASTM D 5147	50 mils
TENSILE STRENGTH	ASTM D 1970	MD95/CD61
ADHESION TO PLYWOOD LB/FT	ASTM D 1970	-
40° F	-	9.5
75° F	-	46.8
THERMAL STABILITY	ASTM D 1970	260F /Pass
LOW TEMPERATURE FLEXIBILITY	ICC AC 48	PASS
TEAR RESISTANCE LB/F	ASTM D 1970	MD124/CD96
PERMEABILITY	ASTM E96	0.08
NAIL SEALABILITY	ASTM D 1970	PASS
TEMPERATURE RANGE	-	40° F to 260° F
FIRE RATING	ASTM E 108	CLASS A
WATERPROOF INTEGRITY OF LAP SEAM	-	PASS
MAX LOAD,LBF/IN	ASTM D 1970	MD95/CD61

SPECIFICATIONS :	DATA
LENGTH PER ROLL	66.7'
WIDTH PER ROLL	36"
WEIGHT PER ROLL	48 LBS
SQUARES PER ROLL	2
ROLLS PER PALLET	25
GR. WEIGHT PER PALLET	1250 lbs

