

EPILAY® PLYSTIK™ SA-250
SYNTHETIC ROOFING UNDERLAYMENT
TECHNICAL DATA SHEET



TEST PROPERTIES	TEST STANDARD	TYPICAL VALUES
UNROLLABILITY	ASTM D1970	NO CRACKING, TEARING OR DAMAGE
Thickness Mils (Nominal)	ASTM D 5147	60 MILS
Max Load, lbf/in	ASTM D 1970	MD32/CD29
ADHESION TO PLYWOOD LB/FT	ASTM D 1970	-
40F	-	4.1
75F	-	13.3
THERMAL STABILITY	ASTM D 1970	250F /PASS
LOW TEMPERATURE FLEXIBILITY	ICC AC 48	PASS
TEAR RESISTANCE LB/F	ASTM D 1970	MD47/CD34
PERMEABILITY	ASTM E96	0.05
NAIL SEALABILITY	ASTM D 1970	PASS
TEMPERATURE RANGE	-	-40F TO 250F
FIRE RATING	ASTM E 108	CLASS A
Waterproof Integrity of Lap Seam	-	PASS

SPECIFICATIONS :	DATA
Length per roll	66.7'
Width per roll	36"
Weight per roll	61 lbs
Squares per roll	2
Rolls per pallet	25
Gr. weight per pallet	1550 lbs

