

PlyStik™ Plus

PEEL & STICK ROOFING UNDERLAYMENT



Technical Data Sheet

TEST PROPERTIES	TEST STANDARD	TYPICAL VALUES
UNROLLABILITY	ASTM D1970	NO CRACKING, TEARING OR DAMAGE
THICKNESS MILS	ASTM D 5147	48 MILS
TENSILE STRENGTH	ASTM D 1970	MD128/CD107
ADHESION TO PLYWOOD LB/FT	ASTM D 1970	-
40° F	-	9.4
75° F	-	13.3
THERMAL STABILITY	ASTM D 1970	250° F /Pass
LOW TEMPERATURE FLEXIBILITY	ICC AC 48	PASS
TEAR RESISTANCE LB/F	ASTM D 1970	MD163/CD184
PERMEABILITY	ASTM E96	0.03
NAIL SEALABILITY	ASTM D 1970	PASS
TEMPERATURE RANGE	-	-40° F to 260° F
FIRE RATING	ASTM E 108	CLASS A

SPECIFICATIONS :	DATA
LENGTH PER ROLL	66.7'
WIDTH PER ROLL	36"
WEIGHT PER ROLL	48 LBS
SQUARES PER ROLL	2
ROLLS PER PALLET	25
GR. WEIGHT PER PALLET	1300 LBS

